

AquaSys® 180 Soluble Support for Additive Manufacturing

Rev 1: 8/21/20

Introducing High Temperature Water Dispersible Support

AquaSys 180 is a high temperature water dispersible thermoplastic material to be extruded, injection molded, or 3D printed.

GENERAL INFORMATION			
Resin	Water Soluble Copolymer		
Filler	Carbohydrate and Polyamide		
Fill level	0-100%		
Uses	Extrusion, Injection Molding, 3D Printing		
Form	Pellets or Filament (1.75mm or 2.85mm)		
PHYSICAL PROPERTIES	TYPICAL VALUE	UNITS	METHOD
Specific Gravity	1.26		ASTM D792
Coefficient Thermal Expansion	4.2E-05	in/in°C	ASTM D696
MECHANICAL PROPERTIES		UNITS	METHOD
Melt Flow Index (260 °C; 5kg)	15.5	g/10min	ASTM D1238
Tensile			ASTM D638
Modulus	983,000	psi	
Strength	18,000	psi	
Elongation @ Break	2.8	%	
Flexural			ASTM D790
Modulus	872,000	psi	
Strength	28,700	psi	
Impact (IZOD)			ASTM D256 / D4812
Unnotched	10.3	ft-lbf/in	
Notched	0.4	ft-lbf/in	
Heat Deflection Temperature (0.45 Mpa)	70	°C	ASTM D648
Vicat Softening (10.0N)	171	°C	ASTM D1525
RECOMMENDED DRYING CONDITIONS			
Oven dry for at least 4-6 hours at 85 °C			
RECOMMENDED MOLDING CONDITIONS			
Barrel temperatures	390 – 435 °F		
Mold temperatures	100 – 130 °F		
STORAGE AND PACKAGING			
Store AquaSys 180 in metallized foil packaging with desiccant. Reseal after use.			

See MSDS/SDS for material handling.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Infinite Material Solutions, LLC. expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product described and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.